Scientific Journal of Control Engineering
Volume 12 Issue 2, December 2025, PP. 7-11

Phase Transformation Behavior and Smart Applications of Shape Memory Alloys

Jiao Luo
Xihua University, 610039

Abstract

Shape memory alloys (SMAs) are unique materials that exhibit the ability to recover their original shape upon heating after being deformed at low temperatures. Due to their remarkable properties, such as high strength, excellent fatigue resistance, and the ability to undergo significant recoverable deformation, SMAs have found extensive applications in various fields, including biomedical devices, robotics, aerospace, automotive industries, and smart textiles. This paper provides a comprehensive overview of the phase transformation behavior and smart applications of SMAs, focusing on the underlying mechanisms, characteristics, and technological advancements in SMA-based devices. It explores the various phases involved in SMA behavior, including the martensitic and austenitic phases, thermoelastic transformations, and stress-induced phase transformations. Furthermore, this paper discusses the applications of SMAs in smart technologies, including their use in medical devices, actuators, sensors, and energy harvesting systems. By exploring the key factors influencing phase transformations, this study highlights the potential of SMAs in designing next-generation smart materials and systems.

Keywords: Shape Memory Alloys; Phase Transformation; Martensitic Phase; Austenitic Phase; Smart Applications; Biomedical Devices; Actuators; Sensors; Energy Harvesting

1 INTRODUCTION

Shape memory alloys (SMAs) are a class of advanced materials that possess the unique ability to return to a predefined shape upon the application of a specific stimulus, typically temperature. This remarkable property is derived from a reversible solid-state phase transformation between two distinct crystalline phases: the high-temperature austenite phase and the low-temperature martensite phase. SMAs have attracted significant attention in the fields of aerospace, automotive, biomedical engineering, and robotics due to their ability to provide actuation, sensing, and self-healing capabilities without requiring external power sources. The motivation behind this study is to explore the fundamental principles behind the phase transformation behavior of SMAs and the underlying mechanisms that enable their smart applications. The ability to control and optimize these materials for specific applications can lead to the development of more efficient, adaptive, and reliable systems, marking a significant advancement in material science.

2 FUNDAMENTALS OF SHAPE MEMORY ALLOYS

2.1 Definition and Characteristics

Shape memory alloys are metallic materials that exhibit the ability to "remember" and recover their original shape after being deformed, provided that the temperature is changed. The unique characteristics of SMAs stem from the distinct phases they undergo during heating and cooling. These phases are generally classified as austenite, which exists at higher temperatures, and martensite, which is stable at lower temperatures. Upon deformation, the martensite phase can be mechanically transformed into a different structure, which is typically more flexible or pliable. The recovery of the original shape occurs when the alloy is heated above its transformation temperature, and the material reverts to its austenitic phase. The key characteristics of SMAs include excellent fatigue resistance, high energy density, and the ability to undergo large reversible deformations[1].

2.2 Phase Transformation Mechanism

The phase transformation in SMAs is primarily driven by changes in temperature, which affect the material's crystal structure. At lower temperatures, the alloy exists in the martensite phase, a low-symmetry phase that can undergo elastic and plastic deformation. When the temperature is increased, the martensite phase gradually transforms into the austenite phase, which has a higher symmetry and more rigid crystal structure. This phase transition is not only temperature-dependent but can also be influenced by factors such as stress and strain. The transformation occurs through a process known as "martensitic transformation," where the atoms in the crystal lattice rearrange in response to the changes in temperature. The reverse transformation, from austenite to martensite, can also be induced by cooling the alloy below a specific temperature, called the martensite start (Ms) temperature.

2.3 Types of Shape Memory Alloys

Shape memory alloys are commonly divided into several categories based on their chemical composition and the specific phases they exhibit. The most well-known SMAs are based on the binary alloy systems of nickel-titanium (NiTi), which has been extensively researched for its excellent shape memory effect and biocompatibility, making it ideal for medical applications. In addition to NiTi, other types of SMAs include copper-based alloys (such as Cu-Zn, Cu-Al-Ni) and iron-based alloys. Each type of SMA has its own unique set of properties, including transformation temperatures, mechanical behavior, and resistance to fatigue and corrosion. Copper-based alloys, for instance, exhibit higher transformation temperatures compared to NiTi alloys but have lower fatigue resistance. Iron-based alloys are known for their potential use in high-temperature applications due to their superior thermal stability. The choice of alloy depends on the specific requirements of the intended application[2].

2.4 Thermomechanical Properties

The thermomechanical properties of shape memory alloys are vital for understanding their behavior and potential applications. These properties include the transformation temperature range, which is the temperature range within which the phase transformation between martensite and austenite occurs. The mechanical properties, such as the Young's modulus, yield strength, and tensile strength, also play an important role in determining the performance of SMAs under stress. SMAs exhibit a unique combination of high recoverable strain and low modulus, which allows them to undergo large deformations without permanent damage. This makes them particularly suitable for applications that require significant strain recovery, such as actuators, robotic systems, and medical devices. Additionally, SMAs are known to have excellent damping properties, which is advantageous in vibration isolation and energy absorption applications.

2.5 Key Factors Influencing the Phase Transformation

Several factors influence the phase transformation behavior in shape memory alloys. The most significant of these is temperature, which directly affects the transformation between martensite and austenite. The transformation temperatures can be adjusted by altering the alloy composition, as different alloying elements influence the phase stability and the critical temperatures (such as the martensite start and finish temperatures). External stress also plays a crucial role in phase transformation, especially in the case of stress-induced martensitic transformations, where the application of stress can promote the formation of the martensite phase even at temperatures where it would not normally occur. Other factors, such as strain rate, loading conditions, and environmental factors like humidity and corrosion, can further influence the transformation and mechanical properties of SMAs. Understanding these factors is essential for designing SMAs with tailored properties for specific applications[3].

3 PHASE TRANSFORMATION BEHAVIOR

3.1 Martensitic and Austenitic Phases

Shape memory alloys exhibit two primary crystalline phases: martensite and austenite. The martensite phase is a low-temperature, low-symmetry structure that allows for deformation under mechanical stress, making it relatively soft and flexible. In contrast, the austenite phase is stable at higher temperatures and exhibits a more rigid,

high-symmetry structure. This phase transformation between martensite and austenite is the core phenomenon behind the shape memory effect. When SMAs are deformed in the martensitic phase and then heated to a temperature above their transformation threshold, they revert to the austenite phase, thereby recovering their original shape. This transformation is reversible, allowing the alloys to function as "smart" materials that can adapt to changing environmental conditions[4].

3.2 Thermoelastic Phase Transformation

Thermoelastic phase transformation in shape memory alloys refers to the reversible, temperature-induced changes between the martensite and austenite phases. This transformation occurs without the need for external mechanical stress, as it is driven purely by temperature variations. The transition from austenite to martensite can occur under cooling, while the reverse transformation—martensite to austenite—takes place upon heating. This unique characteristic allows SMAs to recover their original shape after deformation when exposed to specific thermal conditions. The thermoelastic behavior also grants SMAs the ability to undergo large recoverable strains with minimal energy input, making them ideal candidates for applications such as actuators and medical devices, where precise control over movement is necessary.

3.3 Transformation Temperatures

The transformation temperatures of shape memory alloys are key parameters that determine the functionality of these materials. The two most important transformation temperatures are the martensite start (Ms) temperature and the austenite start (As) temperature. The Ms temperature is the point at which the alloy begins to transform from austenite to martensite upon cooling, while the As temperature is the point at which the transformation from martensite back to austenite begins during heating. These temperatures can be fine-tuned by altering the alloy composition, particularly by varying the proportions of elements such as nickel, titanium, copper, or aluminum. The range between Ms and As defines the material's operational temperature range, and the ability to control this range is critical for tailoring the material to specific applications[5].

3.4 Stress-Induced Phase Transformation

In addition to temperature, stress can also induce a phase transformation in shape memory alloys. Stress-induced martensitic transformation (SIMT) occurs when an external mechanical load is applied to the alloy at temperatures where the material would otherwise be in its austenite phase. Under sufficient stress, the austenitic structure can transform into martensite without any temperature change. This phenomenon is particularly important in applications where SMAs are used for actuation, as the material can be triggered to undergo phase transformation through mechanical force rather than thermal changes. Stress-induced transformations offer enhanced control over the material's behavior, enabling more complex and efficient functionality in robotic systems, sensors, and actuators.

3.5 Kinetics and Hysteresis of Phase Transformation

The kinetics of phase transformation in shape memory alloys refers to the rate at which the material transitions between martensite and austenite under varying conditions of temperature and stress. These transformations are not instantaneous; they depend on factors such as heating/cooling rates and the degree of external stress applied. Furthermore, SMAs exhibit a hysteresis effect, meaning that the path of transformation between phases is not identical for heating and cooling cycles. This phenomenon can lead to a delay or discrepancy between the transformation points during thermal cycling, causing energy losses in certain applications. Understanding the kinetics and hysteresis of phase transformations is crucial for optimizing the performance of SMAs in real-world applications. Methods such as controlling the heating and cooling rates, reducing external stresses, or selecting alloys with minimal hysteresis can be employed to enhance the efficiency of SMAs[6].

4 SMART APPLICATIONS OF SHAPE MEMORY ALLOYS

4.1 Biomedical Applications

Shape memory alloys, particularly nickel-titanium (NiTi) alloys, have found significant applications in the

biomedical field. The biocompatibility, shape recovery properties, and superelasticity of SMAs make them ideal for medical devices such as stents, surgical staples, and orthodontic appliances. For example, self-expanding stents, which are widely used in vascular surgery, are made from NiTi alloys. These stents can expand and contract in response to temperature changes in the body, allowing them to be easily deployed in a compressed form and then expand to their intended size once positioned. Additionally, SMAs are used in various actuators for minimally invasive surgery, where the ability to contract and expand based on thermal stimuli facilitates precise movement in confined spaces.

4.2 Actuators and Sensors in Robotics

Shape memory alloys are increasingly being integrated into robotic systems for their actuation capabilities. SMAs can function as actuators, providing a compact and efficient means of generating motion in robots. The materials' ability to change shape in response to thermal or mechanical stimuli allows them to perform specific tasks, such as gripping, lifting, or adjusting to environmental conditions. Additionally, SMAs are used in sensor applications due to their sensitivity to environmental changes. For instance, SMA-based sensors can detect changes in temperature or pressure by measuring the resulting deformation, offering a high degree of precision and responsiveness. These capabilities make SMAs a valuable addition to soft robotics and autonomous systems, where adaptability and efficiency are critical[7].

4.3 Aerospace and Automotive Applications

In aerospace and automotive industries, shape memory alloys are employed in a variety of innovative applications, ranging from morphing structures to vibration damping systems. In aerospace engineering, SMAs are used in actuators for wing flaps, landing gear systems, and engine components, where the alloys' ability to respond to temperature changes allows for precise control in demanding conditions. For automotive applications, SMAs are used for noise, vibration, and harshness (NVH) control, where they can dampen vibrations or absorb shocks. Furthermore, SMAs are being explored for use in fuel-efficient systems, where their energy-storing capabilities are harnessed to reduce fuel consumption and increase the overall performance of the vehicle.

4.4 Smart Textiles and Clothing

Shape memory alloys also find applications in the field of smart textiles, where they are integrated into fabrics or garments to enable adaptive, responsive functions. For example, SMAs can be used to create fabrics that change shape or adjust their properties in response to external stimuli such as heat, light, or pressure. These textiles can be used in clothing with adjustable fit, temperature-regulating features, or even wearable devices that provide tactile feedback. The combination of flexible, lightweight properties with the ability to respond to environmental changes makes SMAs ideal for next-generation smart clothing and wearable technology[8].

4.5 Energy Harvesting and Structural Health Monitoring

Shape memory alloys have shown potential in energy harvesting applications, where they can convert mechanical energy into electrical energy through their actuation properties. SMAs integrated with piezoelectric materials can generate power from the motion or vibrations of surrounding structures, making them useful for applications such as sensors in remote or inaccessible locations. Additionally, SMAs are increasingly being utilized in structural health monitoring systems. By incorporating SMA-based sensors into infrastructure such as bridges, buildings, or pipelines, it is possible to detect and monitor the deformation or strain of the material over time, providing real-time feedback on the structural integrity of the system. This ability to self-monitor and self-heal makes SMAs a critical component in the development of smart and sustainable infrastructure.

5 CONCLUSION

Shape memory alloys represent a class of materials with extraordinary capabilities that make them ideal for a wide range of applications in both industrial and commercial domains. Through their ability to undergo reversible phase transformations, SMAs offer unparalleled versatility in adapting to changing environmental stimuli such as

temperature, stress, and pressure. The understanding of their phase transformation behavior, including the martensitic and austenitic phases, thermoelastic phase transitions, and stress-induced transformations, is essential for optimizing their use in various applications.

In the biomedical field, SMAs have revolutionized medical device design, particularly in the development of stents, surgical tools, and orthodontic devices, thanks to their biocompatibility and shape recovery properties. Similarly, in robotics and aerospace, SMAs are utilized for precise motion control, actuators, and sensors, enabling innovative solutions for challenging engineering problems. The ability to integrate SMAs into smart textiles and wearable technologies further expands their potential, offering adaptive, responsive materials for clothing and health monitoring systems.

Looking forward, the future of SMAs lies in the continuous exploration of their phase transformation mechanisms, which will lead to further advancements in material design and application techniques. While challenges such as improving energy efficiency, minimizing hysteresis, and controlling transformation temperatures remain, ongoing research is likely to unlock new frontiers in SMA technologies. The integration of SMAs with other advanced materials and systems will likely lead to the development of smarter, more sustainable products in the coming years. The continued evolution of these materials promises transformative impacts on industries ranging from medicine to infrastructure, contributing to the advancement of next-generation smart materials and devices.

REFERENCES

[1] Li L, Yang Z, Xu K, et al. Strain glass state in Ni50.3Ti29.7Hf20 high-temperature shape memory alloy[J].Scripta Materialia,2025,257116449-116449.

[2] Chen L, Oliveira P J, Yan X, et al. Microstructure and Phase Transformation Behavior of NiTiCu Shape Memory Alloys Produced Using Twin-Wire Arc Additive Manufacturing[J].Additive Manufacturing Frontiers,2024,3(2):200132-.

[3] Xi R, Jiang H, Li G, et al. Effect of solution treatment on the microstructure, phase transformation behavior and functional properties of NiTiNb ternary shape memory alloys fabricated via laser powder bed fusion in-situ alloying[J].International Journal of Extreme Manufacturing,2024,6(4):

[4] Ma G, Hu Y, Zhang L, et al. Phase transformation behavior and mechanical properties of NiTi shape memory alloys fabricated by directed laser deposition[J].Materials Science & Engineering A,2024,908146693-.

[5] Liu Q, Feng Y, Liu B, et al. Regulation of microstructure, phase transformation behavior, and enhanced high superelastic cycling stability in laser direct energy deposition NiTi shape memory alloys via aging treatment[J].Materials Science & Engineering A,2024,915147207-147207.

[6] Yuru Z, Daqiang J, Hui Z, et al. Phase transformation behavior and superelasticity of nanocrystalline Ti50Ni50−xCox shape memory alloys[J].Journal of Alloys and Compounds,2024,975172997-.

[7] Rui X, Hao J, Guichuan L, et al. In-situ alloying of NiTiNb ternary shape memory alloys via laser powder bed fusion using pre-alloyed NiTi and elemental Nb powders: Microstructure, phase transformation behavior and functional properties[J].Additive Manufacturing,2024,79103933-.

[8] Li Z, Zhong J, Zhang J, et al. Toward additive manufactured crack-free NiTiCu shape memory alloys with low-hysteresis and tailorable phase transition behavior supported by theoretical design[J].Additive Manufacturing,2024,92104386-104386.